

TECHNICAL DATA

CHARACTERISTICS	VALUE	
Reaction to fire	CLASS A1	
Flexural Strenght	Lower expected value:	6,7 MPa
	Mean value:	12,3 MPa
	Standard deviation :	4,0 MPa
Slip resistance	SRV dry:	pol. = 39 units - honed 120 = 44 units
	SRV wet:	pol. = 16 units - honed 120 = 19 units
Tactility	NPD	
Apparent density	From 2649 to 2672 kg/m3 Open porosity (mean value) 1,30%	